

technical datasheet

General description

TECBOND 267 is a high performance adhesive formulated for Polyofin plastics such as polypropylene and polyethylene. This adhesive has a high heat resistance of 110°C and good low temperature resistance of -30°C.

To achieve a good bond on polypropylene it is important that the bond is made at the highest temperature possible ie > 200°C

Good bonds can be achieved on polyethylene, polypropylene, polycarbonate, nylon, rigid PVC, light gauge metals and polystyrene and many other substrates. All bonds should be tested at least 24hours after assembly at both the high and low temperatures they will be expected to withstand in service.

Due to the unique flexible nature of TECBOND 267 it is only available in 43mm cartridges.

Technical characteristics

Adhesive type: Synthetic polymer based hotmelt

Colour: Light brown Molten tack: High

	12mm	15mm	43mm	СТ	Bulk
Form			43mm x 43mm		
Sticks per kilo (approx)			18		
Carton quantity			10kg		
Pallet weight:			500kg		
Suggested application temperature			180-215°C		
Brookfield viscosity (POW-12-VISC) spindle 27			3000cps		
Ring & ball softening point (ASTM E28)			150°C		
Heat resistance (BS5350 Part H3)			110°C		
Open time			Long		
Low temperature flexibility (tg)			-30°C		
Applicators or hotmelt system	Tec 150-12 Tec 150-12LM Tec 175-12 Tec 175-12LM Tec 250-12 Tec 250-12LM Gastec 100 Gastec 300 Gastec 500 Tec 810-12 Tec 810-12LM	Tec 810-15 Tec 810-15LM	▼ Tec 3150-43	Tec 1050	Bulk tank Spray Jet Slot coater Roller PUR system

F.D.A. approved. All the constituent parts of this adhesive have been approved by the American F.D.A. under C.F.R. 21.175.105 (adhesives) (subject to limitations).

Filename : 267 TDS 1 of 1 Date : 20/09/10

Tecbond Reference	Description	12mm	15mm	43mm	СТ	Bulk
5	High delivery, low viscosity, long open time. Product assembly adhesive.	•		•	•	•
14	High delivery, vary fast setting packaging adhesive.	•	•	•		
1942	Product assembly adhesive for wood and many plastics.	•	•	•		
1X	Low viscosity, wood working & packaging adhesive. Medium open time.	•		•		
213	Economical, general purpose adhesive.	•	•	•		
214	Economical, fast setting, packaging adhesive.	•	•	•		
23	Medium viscosity multipurpose adhesive.	•	•	•		
232	Economical, clear, general purpose adhesive.	•	•	•		
232 Coloured	Coloured, medium open time, general purpose adhesive. Brown, Green, White, Black, Blue, Gold, Silver, Red, Yellow.	•				
232 Glitter	Multicolour, Red, Green, Silver, Gold.	•				
240	High delivery, long open time, multipurpose, clear adhesive.	•	•	•		
246	Clear and black versions, high performance, gap filling, difficult surfaces, dent pulling.	•				
260	High performance, long open time, tough, flexible adhesive.	•	•	•		
265	Long open time product assembly adhesive for smooth and shiny surfaces.			•		
267	High heat resistant, medium open time, product assembly adhesive.			•		
2169	Peelable adhesive, low tack, non-migrating, CD & credit card attachment, glue dots.				•	•
342	High viscosity, fast setting, white adhesive.	•		•		
410	Pallet stabilisation spray adhesive			•		
420	General purpose spray adhesive.			•		
425	High delivery, high performance, spray adhesive.			•		
430	High performance, long open time spray adhesive.			•		
4741	Full pressure sensitive, very aggressive, multipurpose, paper & plastic materials.				•	•
7718	Coloured, low viscosity, potting, encapsulation & knot filling / wood repair polyamide adhesive.	•	•			
7784	High temperature resistant multipurpose polyamide adhesive.	•	•	•		
7785	High temperature & chemical resistant multipurpose polyamide adhesive.	•	•	•		
9010	Reactive hotmelt. Heat & chemical resistant bonds, rigid bond, once set does not reactivate with heat.				•	
9030	Reactive hotmelt. Heat & chemical resistant bonds, flexible bond, once set does not reactivate with heat.				•	
LM44	Lowmelt, fast setting, high performance, white adhesive.	•		•		

Storage Store in a clean dry place at temperatures between 5°C and 30°C with boxes closed. Do not expose to direct sunlight or

localised heat sources such as radiators or hot pipes.

Removal of glue Assembled components can be separated by heating assembly to a temperature slightly above the heat resistance figure.

EVA & Polypropylene: Residues of EVA and polypropylene based hotmelts can be removed from components with white spirit.

Polyamide: Residues of polyamide based hotmelt can be removed from components with acetone.

PUR: Prior to cross linking adhesive can be removed with white spirit or ketone. Once fully cross linked the adhesive cannot be easily

removed.

Please note The information contained on this data sheet is for guidance only. It is the result of careful laboratory evaluations by trained and

qualified staff using British Standard or similar test methods. However, no warranty is expressed or implied regarding the accuracy of the data or the suitability of the adhesive for any specific purpose. In every case, we strongly recommend that the user shall make their own test to determine to their own satisfaction the suitability of the adhesive for their particular purpose. Neither the seller nor manufacturer shall be liable for any injury, loss, damage, direct or consequential arising out of the use or inability to use the product. Further information is always available to help solve your adhesive problems. Should you require

any further information on our adhesives please contact your nearest distributor.

Power Adhesives Limited. 1 Lords Way. Basildon, Essex, SS13 1TN, ENGLAND Main Telephone: +44 (0)1268 885800 Facsimile: +44 (0)1268 885810 E-mail: sales@poweradhesives.com Website: www.poweradhesives.com





Filename : 267 TDS 2 of 2 Date : 20/09/10